

AIREX® T92

GM--TDS-115

Structural and Sustainable**new DATA SHEET 01.2026 - Replaces 01.2025 (GM-TDS-121)****DESCRIPTION**

AIREX® T92 is a closed-cell, thermoplastic and recyclable polymer foam with recycled content, very good mechanical properties, and an outstanding price / performance ratio.

It has an extraordinary resistance to fatigue, is chemically stable and has negligible water absorption. It is thermally stable during high temperature processing and post curing without after expansion or out-gassing. AIREX® T92 is designed for easy use with all resin systems and processing technologies.

AIREX® T92 is ideally suited as a core material for a wide variety of lightweight sandwich structures subjected to static and dynamic loads and/or exposed to elevated temperatures during manufacturing.

CHARACTERISTICS

- Easy to process with all types of resin and lamination processes
- High process temperature up to 150 °C
- Outstanding fatigue strength
- Best-in-class resin uptake with AIREX® SealX¹⁾
- Very high chemical stability
- Good adhesion (skin-to-core bond)
- Excellent long term thermal stability up to 100 °C
- No water absorption, after expansion nor out-gassing
- Recyclable and recycled material (up to 100 % recycled PET)
- Highly consistent material properties independent from variance in color
- Comprehensive material traceability (machine-readable batch information on each foam sheet)

APPLICATIONS

- **Renewable energy:** Blades (shear webs & shells), nacelles
- **Marine:** Decks, hull sides, superstructures, bulkheads, transoms, interiors
- **Industrial:** Covers, containers, local reinforcements, x-ray tables, sporting goods
- **Automotive:** Truck body parts, floors

PROCESSING²⁾

- Contact molding (hand/spray)
- Vacuum infusion
- Resin infusion / injection (VARTM / RTM)
- Adhesive bonding
- Pre-preg processing
- Compression molding (GMT, SMC)
- Thermoforming

¹⁾ AIREX® SealX is a controlled surface treatment for minimum resin consumption

²⁾ for details, please refer to AIREX® Processing Guidelines

MECHANICAL PROPERTIES												
Typical properties		Unit (metric)	Value ¹⁾	AIREX® T92.70	AIREX® T92.80	AIREX® T92.100	AIREX® T92.110	AIREX® T92.130	AIREX® T92.150	AIREX® T92.200	AIREX® T92.230	AIREX® T92.280 ³⁾
Density ⁵⁾	ISO 845	kg/m ³	Nominal Typ.range	73 68 - 78	85 80 - 90	100 95 - 105	110 100 - 115	135 127 - 142	150 143 - 155	210 200 - 220	230 220 - 240	280 260 - 295
Compressive strength perpendicular to the plane	ISO 844 ASTM C365	N/mm ²	Typical Minimum	0.9 0.75	1.3 1.1	1.6 1.35	1.7 1.5	2.3 1.9	2.6 2.3	3.8 3.2	5.0 4.3	6.2 5.6
Compressive modulus perpendicular to the plane	ASTM C365	N/mm ²	Typical Minimum	60 45	75 60	90 65	95 70	110 90	130 110	180 150	215 180	250 230
	ISO 844 B	N/mm ²	Typical	70	90	100	110	135	150	205	230	280
Tensile strength perpendicular to the plane	ASTM C297	N/mm ²	Typical Minimum	1.5 1.1	1.9 1.4	2.3 1.5	2.3 1.55	2.35 1.85	2.5 2.0	2.85 2.3	3.1 2.5	tbd
Tensile modulus perpendicular to the plane	ASTM C297	N/mm ²	Typical Minimum	85 75	90 80	110 90	115 95	170 130	180 150	230 190	250 200	tbd
Shear strength (both directions)	ISO 1922	N/mm ²	Typical Minimum	0.58 0.48	0.72 0.65	0.9 0.75	0.95 0.80	1.3 1.1	1.5 1.25	2.0 1.6	2.7 1.7	3.0 1.9
Shear modulus (both directions)	ISO 1922	N/mm ²	Typical Minimum	15 11	22 16	24 20	26 22	33 27	42 36	55 48	73 60	82 70
Shear elongation (both directions)	ISO 1922	%	Typical Minimum	20 13	23 12	20 10	15 10	12 8	10 5	6 4	5 3	5 3
Thermal conductivity at 10 °C	EN 12667	W/m.K	Typical	0.037	0.030	0.034	0.035	0.037	tbd	0.045	tbd	tbd
Colour	Visual			variable ⁶⁾								
Standard sheet	Width ²⁾	mm ± 5		1220	1220	1220	1220	1220	1220	1220	1220	1005
	Length ²⁾	mm ± 5		2440	2440	2440	2440	2440	2440	2440	2440	2440
	Thickness ⁴⁾	mm ± 0.5		2 to 100	2 to 100	2 to 100	2 to 100	2 to 100	5 to 100	5 to 100	5 to 100	5 to 100

Finishing Options, other dimensions and closer tolerances upon request. ¹⁾ Statistical minimum values; test sample thickness 20 mm except thermal conductivity (50 mm). ²⁾ Alternative width 610 mm, alternative length 1220 mm. ³⁾ Preliminary data. ⁴⁾ Sheets with thickness lower than 5 mm and densities under 130 kg/m³ have stricter tolerance of +/-0.2 mm and dedicated for micro-sandwich applications; they are marked as AIREX® TM92. ⁵⁾ SealX adds approx. 2 kg/m³. ⁶⁾ Depends on raw material batch.

The data provided gives approximate values for the nominal density and DNV-GL minimum values according to DNV-GL type approval certificate. Typical values are based on statistics over time. The information contained herein is believed to be correct and to correspond to the latest state of scientific and technical knowledge. However, no warranty is made, either expressed or implied, regarding its accuracy or the results to be obtained from the use of such information. No statement is intended or should be construed as a recommendation to infringe any existing patent.