

# Safety data sheet for AIREX® TegraCore™

According to Regulation (EC) No. 1907/2006 & GHS

Page 1 of 3

1<sup>st</sup> issue: March 9, 2020  
GM--SDS-028

<p><b>1. Identification of substance / preparation and of the company</b></p> <p>AIREX® TegraCore™ Rigid foam</p> <p>Use of substance / preparation: Core material in sandwich constructions</p> <p><i>Company identification:</i> Airex AG 5643 Sins, Switzerland Tel +41 41 789 66 00 Fax +41 41 789 66 60</p>
<p><b>2. Hazards identification</b></p> <p>AIREX® TegraCore™ does not constitute any risk to public health and environment if it is used as intended.</p> <p>Fine dust is produced while sawing, milling, grinding and sanding.</p> <p>Irritant fumes may be produced while thermoforming.</p>
<p><b>3. Composition / Information on ingredients</b></p> <p>Rigid polymeric foam on the basis of Polyphenylsulfone (PPSU), foamed using titanium dioxide.</p>
<p><b>4. First aid measures</b></p> <p><i>Inhalation of processing fumes:</i> Move victim to fresh air; obtain medical attention if irritation persists.</p> <p><i>Inhalation of gases in case of fire:</i> Move victim to fresh air and obtain medical attention.</p> <p><i>Skin contact:</i> Cool skin rapidly with cold water after contact with hot polymer; do not peel polymer from the skin and obtain medical attention if needed.</p> <p><i>Eye contact:</i> Flush with water; obtain medical attention if irritation persists.</p> <p><i>Ingestion:</i> No special measures required. Seek medical attention if symptoms develop. Avoid mouth contact with an unconscious person.</p>
<p><b>5. Fire-fighting measures</b></p> <p>Suitable extinguishing media: Foam, water or water spray, extinguishing powder, carbon dioxide.</p> <p>Extinguishing media which must not be used: not known.</p> <p>Hazardous combustion products: Combustible materials. Melting polymer may propagate fire and heating can release hazardous gases.</p>
<p><b>6. Accidental release measures</b></p> <p>Avoid dust formation.</p>
<p><b>7. Handling and storage</b></p> <p><i>Handling:</i> Take measures to prevent possibility of electrostatic charge. Ensure all equipment is electrically grounded before beginning transfer operations. To avoid thermal decomposition do not overheat.</p> <p><i>Storage:</i> Stow away from sources of ignition. Keep away from hot surfaces. Danger of electrostatic charges when stored in very dry areas. Avoid dust formation. Do not overheat to avoid thermal decomposition.</p>

[www.3Acorematerials.com](http://www.3Acorematerials.com)

Europe | Middle East | India | Africa  
Airex AG  
5643 Sins, Switzerland  
T +41 41 789 66 00 | F +41 41 789 66 60  
[corematerials@3AComposites.com](mailto:corematerials@3AComposites.com)

North America | South America  
Baltek Inc.  
High Point, NC 27261, USA  
T +1 336 398 1900 | F +1 336 398 1901  
[corematerials.americas@3AComposites.com](mailto:corematerials.americas@3AComposites.com)

Asia | Australia | New Zealand  
3A Composites (China) Ltd.  
201201 Shanghai, China  
T +86 21 585 86 006 | F +86 21 338 27 298  
[corematerials.asia@3AComposites.com](mailto:corematerials.asia@3AComposites.com)

# Safety data sheet for AIREX<sup>®</sup> TegraCore<sup>™</sup>

According to Regulation (EC) No. 1272/2008

Page 2 of 3

1<sup>st</sup> issue: March 9, 2020  
GM--SDS-028

<b>8.</b>	<b>Exposure control / personal protection</b>	
	<i>Exposure limit values:</i>	Not applicable.
	<i>Exposure controls:</i>	The use of gloves, protective goggles, dust masks, use of dust extraction equipment and long-sleeved clothing is recommended for sawing, milling, grinding and sanding. For thermoforming, the workplace should be continuously supplied with fresh air. Where necessary, a respiratory protection is recommended. When handling hot material, heat resistant gloves are recommended.
<b>9.</b>	<b>Physical and chemical properties</b>	
	<i>Physical state / form:</i>	Solid foam sheet.
	<i>Colour:</i>	White.
	<i>Softening point temperature:</i>	approx. 220 °C      ISO 6721-2
	<i>Decomposition temperature</i>	> 430 °C
	<i>Flash ignition temperature</i>	n/a
	<i>Density:</i>	53 kg/m <sup>3</sup> ISO 845
	<i>Solubility:</i>	Negligible water solubility.
<b>10.</b>	<b>Stability and reactivity</b>	
	<i>General information:</i>	Stable under normal conditions.
	<i>Conditions to avoid:</i>	Heat, flames and sparks, avoid dust formation. The normal temperature for processing this resin exceeds the decomposition and/or ignition temperature of some other polymeric resins, such as polyacetal, polyvinyl chloride (PVC), polypropylene, etc. If PVC or any other resin with a decomposition temperature below 371°C / 700°F is moulded or handled in your equipment, these materials can rapidly decompose and/or react with this resin at the temperatures used to process this resin. Inadvertent contamination of this resin with these materials from the material handling system or other equipment can result in a rapid, possibly violent release of decomposition fumes, when the contaminated material is brought to processing temperature. To avoid, thoroughly clean moulding and other processing equipment prior to changeover and prevent cross contamination of material handling systems.
	<i>Materials to avoid:</i>	Not applicable.
	<i>Dangerous decomposition products:</i>	Sulphur oxides. Carbon monoxide (CO). Hydrocarbons.
<b>11.</b>	<b>Toxicological information</b>	
	<i>Toxicological tests:</i>	No data available.
	<i>Experience with man:</i>	
	<i>Skin contact:</i>	No data available.
	<i>Eye contact:</i>	No data available.
	<i>Inhalation:</i>	No data available.
	<i>Ingestion:</i>	No data available.
<b>12.</b>	<b>Ecological information</b>	
	<i>Ecotoxicity:</i>	No data available.
	<i>Mobility:</i>	No data available.
	<i>Persistence and degradability:</i>	No data available.
<b>13.</b>	<b>Disposal considerations</b>	
	Subject to legislation by local authorities, the product can be disposed together with domestic refuse and industrial waste.	

# Safety data sheet for AIREX<sup>®</sup> TegraCore<sup>™</sup>

According to Regulation (EC) No. 1272/2008

Page 3 of 3

1<sup>st</sup> issue: March 9, 2020  
GM--SDS-028

## 14. Transport information

Railroad	RID	No restriction.
Road	ADR	No restriction.
Sea	IMDG Code	No restriction.
Air	ICAO-TI/IATA-DGR	No restriction.

## 15. Regulatory information

AIREX<sup>®</sup> TegraCore<sup>™</sup> rigid plastic foam does not require marking under the following directives or is not concerned by the following regulations:

- United States TSCA Inventory.
- Canadian Domestic Substances List (DSL).
- EU. European Registration, Evaluation, Authorisation and Restriction of Chemical (REACH).
- Japan. CSCL – Inventory of Existing and new Chemical Substances.
- China. Inventory of Existing and new Chemical Substances in China (IESCS).

## 16. Other information

This is an initial issue of the TegraCore<sup>™</sup> Safety Data Sheet.

The information given in this material safety data sheet is accurate to the best of our knowledge, but without any guarantee. It is given in good faith based on the current state of knowledge and experience. It is issued in respect of safety requirements and does not purpose to provide information on the quality of the material.